


Technical Data Sheet

5571 Platinum Conductor

Material # 1148039



Product Description

5571 Platinum Conductor is designed to be co-fired with alumina tape at high temperatures. Applications include a heater in planar sensors.

5571 is formulated to be Lead free and Cadmium free. The term “free” means that Lead and Cadmium have not been intentionally added to the product. However, trace amounts may be present.

An ESL-Electro Science Laboratory Legacy Product.

Typical Formulation Properties

Viscosity: $80 \pm 8 \text{ Pa}\cdot\text{s}$ at $25.0 \pm 0.2^\circ\text{C}$, when measured using a Brookfield HBT cone/plate viscometer at 38.4/sec shear rate.

Thinner: 438(Material # 1148613)

Storage and Shelf Life: This product should be stored in tightly sealed containers at 20°C to 25°C , in a dry place away from direct sunlight. The shelf life of a factory sealed container is a minimum 6 months from date of shipment when properly stored.

Typical Processing Recommendations

Printing: 325 mesh stainless steel screen with a 20 to 30 μm thick emulsion.

Leveling: 5 to 10 minutes at room temperature.

Drying: 10 to 15 minutes at 80°C with forced air flow and exhaust.

Firing: Optimum results are obtained by firing at a peak temperature of $1500^\circ\text{C} \pm 10^\circ\text{C}$ for 120 minutes.

Substrate of Calibration: 44000 Tape (Material# 1148457)

Typical Fired Properties

Resistivity: (2 layers cofired on 44000 (Material # 1148457), normalized to $25\mu\text{m}$ fired) 18 to $20\text{m}\Omega/\square$.

Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.

Copyright © 2016 Ferro Corporation

Technical Data Sheet

