

Technical Data Sheet

Conductive Silver Lacquer 62900341

Product description

62900341 is an Ag air-drying conductive lacquer for a large number of applications. It can be used in all cases where excellent electrically conductive layers are required (plastics, papers, wood, glasses, ceramics, metals, etc.).

62900341 is formulated and processed to be RoHS compliant.

Working Conditions

The application of the paste is recommended as follows:

Redispersion: Please ensure that the paste is carefully homogenized before use. We recommend to use an electrical shaker or propeller stirrer at appr. 300 rpm for 10 min.

Thinner: This paste has a ready to use viscosity. If viscosity adjustment is necessary please use our thinner 68100222.

Application: Paste can be applied by brush, spray gun or dipping.

Drying: 30 min at 20 °C, air or
10 min at 80 °C, air forced oven or
5 min at 150 °C, air forced oven
Drying at any temperature up to 150 °C is possible.

Storage conditions: To avoid sedimentation of the solids and to prevent ageing of the paste we recommend storage conditions between 4 – 20 °C. If longer storage than 12 months is necessary we strongly recommend to store cool between 4 – 8 °C.

Product properties	Methods	Data
Silver content	At 800 °C, 10 minutes	45.0 ± 0.2 %
Viscosity	Flow cup – system, DIN 53211 Ø 3 mm at 25 °C	30 – 35 s run out time
Resistivity		30 - 60 mΩ /square; 10 µm thickness



Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.