



## **Ceramic Powders and Formulations for Passive Components**Barium Titanate Powder Products

## **Application**

Ferro is a leading manufacturer of barium titanate powder products fabricated by solid state synthesis. These are used for a variety of electronic component applications that can include single & multilayer ceramic capacitors, piezoelectric

devices, EL coatings, embedded capacitors, composite polymer films and many others.

All products are Pb/Cd free and formulated and processed to be RoHS compliant.

## **Barium Titanate Products**

Product Code			219-6A	Ticon C	Ticon P
Chemical Formula			BaTiO <sub>3</sub>	BaTiO <sub>3</sub>	BaTiO <sub>3</sub>
BaO + SrO : TiO2 Mole Ratio			0.994	0.981	0.997
Particle Size Distribution	D90	μm	2.1	3.2	4.0
	D50	μm	1.3	1.5	1.8
	D10	μm	0.8	0.7	0.6
Surface Area		m²/g	2.1	2.0	2.0
Loss on Ignition		wt-%	< 0.5	< 0.5	< 0.5
True Density <sup>1</sup>		g/cc	6.0	6.0	6.0
Typical Total Impurities		wt-%	< 0.1	<1	<1

<sup>1</sup> Per Helium Pycnometer



## **Limitation of Warranty and Liability**

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale shall control.

Ferro Corporation | 6060 Parkland Blvd, Suite 250 | Mayfield Heights, OH 44124 | USA

P 315.227.5278 | E ele@ferro.com | W ferro.com | July 2019