

Technical Data Sheet

Solutions for Decoration

L 412 - Covercoat

Application	Due to its excellent combustibility and depolymerization, the very flexible covercoat L 412 can be used for decorations on glass, porcelain, ceramics and enamel. L 412 is not suitable for the heat-release process. For recommended heat-release products please refer to our Media Guide
Printing Properties	High printing speeds can be achieved with L 412, without any cobwebbing or blistering, due to the well-balanced solvent composition. As L 412 is a flowing covercoat, however, care must be taken when using dryers with a continuous flow of air to avoid the formation of beads caused by too thick a print, or a horizontal pre-drying zone must be used before running through the dryer.
Film characteristics	After the solvents have evaporated, L 412 produces an easy-to-handle, durable and flexible film with good extensibility. The recommended minimum dry film thickness should be some 23 µm.
Application errors	If the recommended processing temperature of 20-25 °C is not observed, i.e. the temperature is lower, cobwebbing may occur when printing, the dry film thickness may be insufficient and there may be pinholes in the dry film due to poor levelling properties.
Storage	L 412 should be stored in the drums in which it was originally supplied by FERRO in a dry place at room temperature (15-25°C). Always seal opened drums carefully as the composition of the product changes when solvents evaporate from open drums. When this storage recommendation is observed, the minimum shelf life in unopened original drums is 2 years.
Environment	Waste material treatment, environmental health and safety protection has to follow the local regulations and legislation.

Field of application	glass, porcelain, ceramics, enamel
Processing	with automatic and semi-automatic screen printing equipment
Appearance	clear or colored, transparent liquid
Composition	polyacrylates; plasticizer; solvents
Viscosity at 23°C [mPa*s]	1500 at 50 1/s ; 1550 at 200 1/s
Degree of thixotropy	none
Consistency	flowing
Density at 20°C [g/cm³]	0,95
Non-Volatile parts (nvp) [%]	42
Flash point according ISO 3680 [°C]	+47
Recommended screen material	PET: 21-140 to 24-120 or corresponding steel mesh
Blocking stability	not tack-free, interlayer wax paper required
Minimum dry film thickness [µm]	23
Drying figures TZ according to Mettler	TZ 10: 40 ; TZ 100: 630
Recommended working temp. [°C]	20 - 25
Recommended rel. humidity [%]	55 - 60
Thinner	--
Cleaner	80 452

Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.