

A 6 Thixotropic Covercoats for Indirect Screen Printing

Product-number	Viscosity [mPa*s] 1. D=50 1/s 2. D=200 1/s at 23°C, approx.	Extensibility index	nvp [%] approx.	Drying Figures TZ	Recommended dry film-thickness in µm	Decoration of
L 406/ THIX	1. 1950 2. 1800	95	42	TZ10 = 40 TZ90 = 650	23	glass porcelain ceramics enamel
L 409/3 Antiblock	1. 2300 2. 2100	105	43	TZ10 = 45 TZ90 = 860	23	glass porcelain ceramics enamel
L 412/THIX	1. 1750 2. 1600	45	42	TZ10 = 40 TZ90 = 630	23	glass porcelain ceramics enamel

The technical data sheets of the individual products can be found in the Resource Center.

Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at www.ferro.com. In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.